



TECHNICAL DATA

GLASSFLO MPT SPRAY

Mould Pre-treatment Spray

TECHNICAL DATA

Description

ROCOL Glassflo MPT Spray is a dry-film blank mould pre-treatment specially formulated to remove the need for manual swabbing of moulds during start-up, so giving consistent running conditions. ROCOL Glassflo MPT Spray can also be applied to blow moulds, bottom plates, neck rings and other related equipment.

Outstanding Features

- Clean, air cured, dry coating - requires no baking.
- Prevents adhesion of ware to moulds.
- Promotes excellent glass distribution.
- Cost efficient through reduced mould dope usage.
- Consistent quality through even film.

Directions for Use

Ensure surfaces are clean, dry and free from oil or grease.

Apply a thin, even coat from a distance of 15-20cm.

Touch dry in approximately 1 minute.

For best results allow to cure at room temperature for 2-4 hours.

After use invert can and spray until nozzle is clear.

Lightly burnish the applied film for an excellent finish to ware.

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: 0113 232 2600 Fax: 0113 232 2760

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW inc

The information in this publication is based on our experience and reports from customers.
There are many factors outside our control and knowledge which effect the use and performance of our products
for which reason the information in this publication is given without responsibility

Technical Data (typical values)

<i>Appearance:</i>	<i>Thin, grey/black film.</i>
<i>Solid Lubricant:</i>	<i>Graphite</i>
<i>Binder:</i>	<i>Organic Resin</i>
<i>Solvent:</i>	<i>Non-chlorinated</i>
<i>Storage:</i>	<i>Storage temperature should be kept below 50°C. Storage area should be out of direct sunlight.</i>

Pack sizes and part codes

400ml part code 78871

Health and Safety

Safety data sheet is available from the Customer Service Department, ROCOL Lubricants, ROCOL House, Swillington, Leeds, LS26 8BS, England.

Telephone: 0113 232 2700, (When calling from outside UK: 44 113 232 2700).

Fax: 0113 232 2760, (When faxing from outside UK: 44 113 232 2760).

Issue: Glassflo MPT Spray TDS 7887
Date: Jan-04

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: 0113 232 2600 Fax: 0113 232 2760

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW inc

The information in this publication is based on our experience and reports from customers.
There are many factors outside our control and knowledge which effect the use and performance of our products
for which reason the information in this publication is given without responsibility

TECHNICAL DATA