



# PIPESEAL PTFE LIQUID

**Flexible, setting pipe sealant for metallic threaded joints  
Primarily for Air, Water & Steam**

## FEATURES

- Ø Temperature range  $-50^{\circ}\text{C}$  to  $250^{\circ}\text{C}$
- Ø Suitable for pressures up to 400 psi (28 bar)
- Ø Only use where good mechanical sealing exists
- Ø Pressure test after a minimum of 6 hours
- Ø Sets hard but flexible
- Ø Resists thermal expansion
- Ø Can replace PTFE thread tape in many applications

## DIRECTIONS FOR USE

- Ø Do not apply in sub-zero temperatures
- Ø Shake well before use
- Ø Ensure surfaces are clean and free of contaminants
- Ø Apply with a brush to both surfaces
- Ø Assemble within 5 minutes
- Ø Pressure test after a minimum of 6 hours at ambient ( $20-25^{\circ}\text{C}$ )
- Ø Lower temperatures will extend drying time

## Technical and Safety Data Sheets are available from:

**Fax Back Facility** : +44 (0)113 232 2770  
**Web Site** : [www.rocol.com](http://www.rocol.com)  
**Customer Service** : +44 (0)113 232 2700

Issue Aug-07c

### **ROCOL Lubricants**

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

[www.rocol.com](http://www.rocol.com)

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers.  
There are many factors outside our control or knowledge which affect the use and performance  
of our products, for which reason it is given without responsibility.



# PIPESEAL PTFE LIQUID

## TECHNICAL DATA (typical values)

Appearance	White emulsion
Base type	Organic resin & solvent
Solids	PTFE
Temperature	-50°C to 250°C
Pressure	Up to 400 psi (28 bar)
Suitable applications	Air Water Steam Mineral & Vegetable oils Paraffin & White Spirit Ammonia refrigerant
Storage	Store away from sources of heat or ignition. Storage area should be: well ventilated. under cover. Storage and transfer equipment should be adequately earthed and bonded to prevent the accumulation of static charges.
Pack sizes	300g

Issue Aug-07c

2

### **ROCOL Lubricants**

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

[www.rocol.com](http://www.rocol.com)

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA